

4. (amended) The web material of claim 1, having a basis weight of 9 to 19 g/m².
6. (amended) [A fibrous non-woven non-heat seal porous web material consisting of 0.5 to 25 percent by weight of] The web material of claim 1, wherein the synthetic material comprises synthetic pulp having a micro-fibrillar structure with natural fibers comprising the remainder of said web material.
8. (amended) The web material of claim 1, wherein the synthetic material is selected from [the group consisting of] polyethylene, polypropylene, polyester and mixtures thereof.
9. (amended) The web material of claim 1 comprising [a] first phase constituents comprising at least one of synthetic material or natural fibers and [a] second phase constituents comprising at least one of synthetic material or natural fibers, wherein the constituents of each phase are substantially homogeneously distributed throughout the single wet laid layer.

Cancel claim 10 without prejudice.

11. (amended) The web material of claim 1, wherein the natural fibers [consist of] comprise long natural fibers.
12. (amended) The web material of claim 1 having a dry crimp strength at least twenty percent greater than a fibrous non-woven non-heat seal porous web material consisting of the same [composition] fibers but without the synthetic material.
- 15. (amended) An infusion package comprising the web material of claim 1, said web material being mechanically folded without heat sealing to enclose a beverage precursor material therein.
16. (amended) A process of making a [single layer] fibrous non-woven non-heat seal porous web material of enhanced dry crimp strength comprising:

forming a slurry of natural fibers;
adding synthetic materials [in an amount insufficient to form a heat seal bond] to said slurry to form a furnish;
wet laying said furnish to form a single layer web; and
drying said web to form said web material, wherein the amount and activation of synthetic materials in the web material provides the web material with a heat seal seam strength that is not acceptable for use as a heat sealable, infusion packaging web material.

Cancel claim 19 without prejudice/

Please add the following claims:

--21. The process of claim 16 including the steps of forming an additional furnish comprising at least one of synthetic material or natural fibers and wet laying one of the furnishes over the other furnish to form the single layer web, wherein the synthetic material and natural fibers are substantially homogeneously distributed throughout the single layer web.

22. A non-woven porous web material, wherein:
the web material consists of a single, wet laid layer;
the web material has a basis weight from about 9 g/m² to about 19 g/m²;
the web material is acceptable for use as infusion packaging web material;
the web material has a heat seal seam strength that is unacceptable for use as a heat sealable, infusion packaging web material; and
the web material comprises a substantially homogeneous mixture of about 0.5 percent to about 25 percent by weight of synthetic material selected from polyethylene, polypropylene, polyester and mixtures thereof and about 75 percent to about 95.5 percent of natural fibers.--